



Preliminary Data sheet

Tailor made Engineering Plastic

Product: Kaycom PA 66 110/160 Black 94200

Injection moulding easy flowing grade PA66

TYPICAL PROPERTIES ①	Standard	Unit	TYPICAL VALUE	
			Dry	Conditioned
PHYSICAL:				
Density	ISO 1183	g/cm ³	1.13	--
Moisture absorption (23°C / 50% RH)	ISO 62	%		
Melt Volume Rate, MVR at 275°C/5kg	ISO 1133	cm ³ /10 min		--
Filler content		%	0	--
MECHANICAL:				
Tensile Modulus	23°C ISO 527 -2	Mpa	3600	1500
Tensile Stress at break	23°C ISO 527 -2	Mpa	87	58
Tensile Strain, yield	23°C ISO 527 -2	%	4.2	20
Flexural Modulus	23°C ISO 178/A	MPA		
IMPACT:				
Izod Impact, notched	23°C ISO 180 - 1A	KJ/m ²	4.5	12
Charpy impact unnotched	23°C ISO 179	KJ/m ²		
Charpy notched impact strength	23°C ISO 179	KJ/m ²		
THERMAL:				
Vicat softening temperature	ISO 306	°C		
Heat deflection temperature HDT A	ISO 75-1,2	°C	75	
Flammability UL 94	UL 94	mm	HB	--
ELECTRICAL:				
Volume Resistivity	IEC 60093	Ohm-cm		
Dielectric Strength in oil 0,8 mm	IEC 60243	KV/mm		
PROCESSING PARAMETERS / Injection moulding				
Drying Temperature		°C	80	
Drying Time		Hrs	2 - 6	
Melt Temperature		°C	280 - 300	
Mould Temperature		°C	80 - 90	

Version: 10 April 2014

① Typical values only. Variations within normal tolerances are possible for various colours. They are based on our general experience and given in good faith, but we are unable to accept responsibility in respect of factors which are outside our knowledge or control

Kays Kft. Quality system is validated / certificated to ISO 9001 - 2008 by TÜVReinland InterCert Kft.