



Preliminary Data sheet

Tailor made Engineering Plastic

Product: Kaycom PA 6.6 112-H/GF30 Black 94220

TYPICAL PROPERTIES ①	Standard	Unit	TYPICAL VALUE
PHYSICAL			
Density	ISO 1183	g/cm ³	1.36
Water Absorption, (23°C /sat)	ISO 62	%	
Moisture absorption (23°C / 50% RH)	ISO 62	%	
Melt Flow Rate, 275°C/5 kg	ISO 1133	g/10 min	
Melt Volume Rate, MVR at 275°C/5kg	ISO 1133	cm ³ /10 min	
Filler content		%	30
MECHANICAL			
Tensile Modulus, 1 mm/min	ISO 527	Mpa	9000
Tensile Stress at break, 5 mm/min	ISO 527	Mpa	170
Tensile Strain, yield, 5 mm/min	ISO 527	%	3
Flexural Modulus, 2 mm/min	ISO 178	MPA	
IMPACT			
Charpy unnotch (23°C)	ISO 179	KJ/m ²	50
Charpy notched impact (23°C)	ISO 179	KJ/m ²	6.5
THERMAL			
Vicat softening temperature	ISO 306	°C	
Heat deflection temperature HDT A	ISO 75	°C	
Flammability UL 94	UL 94	mm	HB
ELECTRICAL			
Volume Resistivity	IEC 60093	Ohm-cm	
Dielectric Strength in oil 0,8 mm	IEC 60243	KV/mm	
PROCESSING PARAMETERS / Injection moulding			
Drying Temperature		°C	60 - 90
Drying Time		Hrs	4 - 10
Melt Temperature		°C	280- 300
Mould Temperature		°C	80 - 120

Version: 24 March 2014

① Typical values only. Variations within normal tolerances are possible for various colours. They are based on our general experience and given in good faith, but we are unable to accept responsibility in respect of factors which are outside our knowledge or control

Kays Kft. Quality system is validated / certificated to ISO 9001 - 2008 by TÜVReinland InterCert Kft.

© 2014 Kays Kft. Győr Hungary